



시험성적서

1. 성적서 번호 : CT20-015531K
2. 의뢰자
 - 업체명 : 주식회사 현대엘앤씨
 - 주소 : 서울특별시 중구 을지로5길 26, 7, 8층 (수하동, 미래에셋 CENTER 1)
3. 시험기간 : 2020년 02월 03일 ~ 2020년 03월 03일
4. 시험성적서의 용도 : 품질관리
5. 시료명 : 칸스톤 (Hanstone)
6. 시험방법
 - (1) KS F 4739:2016

확인	작성 자명	김응구	기술책임자 성명	강병철
비고 : 1. 이 성적서는 KS Q ISO/IEC 17025 및 KOLAS 인정과 관련이 없으며, 의뢰자가 제시한 시료 및 시료명에 한정된 결과로서 전체제품에 대한 품질을 보증하지는 않습니다. 2. 이 성적서는 홍보, 선전, 광고 및 소송용으로 사용될 수 없으며, 용도 이외의 사용을 금합니다. 3. 이 성적서의 일부만을 발췌하여 사용한 결과는 보증할 수 없습니다. 4. 이 성적서의 진위여부는 홈페이지(www.kcl.re.kr)에서 확인 가능합니다.				

2020년 03월 03일

한국건설생활환경시험연구원



결과문의 : 28116 충청북도 청주시 청원구 오창읍 연구단지 40 충북테크노파크 선도기업관 101호 ☎ (043)718-9054

총 2페이지 중 1페이지

양식TQP-12-01-03(1)



시험성적서

성적서번호 : CT20-015531K

7. 시험결과

1) 칸스톤 (Hanstone)

시험항목	단위	시험방법	시험결과	비 고	시험장소
비중	-	(1)	2.32	-	A
흡수율	%	(1)	0.04		
휨강도	N/mm ²	(1)	43.1		
내오염성(3% 염산)	-	(1)	이상없음		
내오염성(3% 수산화나트륨)	-	(1)	이상없음		
국부압축강도	N/mm ²	(1)	5.2		B
충격강도	-	(1)	이상없음		
내마모성(광택감소율)	%	(1)	18.5		

※ 시험장소

A : 대전광역시 유성구 가정북로 26-34

B : 세종특별자치시 부강면 부강금호로 37



—— 끝 ——






TEST REPORT

1. NO : CT20-015531E
2. Client
 - Name : HYUNDAI L&C
 - Address : 26, Eulji-ro 5-gil, Jung-gu, Seoul, 04539 Republic of KOREA
3. Date of Test : 2020.02.03 ~ 2020.03.03
4. Use of Report : Quality Control
5. Test Sample : HANSTONE
6. Test Method
 - (1) KS F 4739:2016

Affirmation	Tested By Name : Kim Eung Gu 	Technical Manager Name : Kang Byung Chul 
This report is not accredited by KOLAS. Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. The results of using only a portion of this report cannot be guaranteed. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr).		

2020.03.03

Korea Conformity Laboratories President Yoon, Kap Seok 

Result Inquiry : 40, Yeongudangi-ro, Ohchang-Eup, Cheongwon-Gu, Cheongju-si, Chungbuk, Korea (82-43-718-9054)



TEST REPORT

No : CT20-015531E

7. Test Results

1) HANSTONE

Test Item(s)	Unit	Test Method	Test Results	Remark	Loc.
Specific gravity	-	(1)	2.32	-	A
Absorption	%	(1)	0.04		
Bending strength	N/mm	(1)	43.1		
Stain resistance(3% Hydrochloric acid)	-	(1)	Pass		
Stain resistance(3% Sodium hydroxide)	-	(1)	Pass		
Local compression strength	N/mm	(1)	5.2		B
Impact strength	-	(1)	Pass		
Abrasion resistant	%	(1)	18.5		

※ Location

A : 26-34, Gajeongbuk-ro, Yuseong-Gu, Daejeon, Korea

B : 37, Buganggeumho-ro, Bugang-myeon, Sejong-si, Korea

—— End of Report ——

